

Maleic Copolymer Syntan

Aspect	: Clear viscous liquid
Basis	: Maleic Acrylic Copolymer
Solid content	: 29±1.0%
pH	: In 10% aqueous solution, 7.0-8.0
Solubility	: Good
Light fastness	: Excellent
Stability	: Stable to Neutral salts, Acids and Bases in usual concentrations in tannery. Compatible with Synthetic and Vegetable tanning agents and Dyes.

PROPERTIES :

- Has an excellent distribution property that protects leather from drawn grain.
- Due to its polymeric nature, it helps in achieving a unique combination of “Tight Grain with Mellow Handle”.
- Is suitable for Upholstery leather, as it maintains inner softness & body even after wet toggling.
- It has a significant application in making of Shoe uppers with good inner softness and tight grain.
- Is light fast in nature, so can be used in any kind of white, pastel and other dark colored Leather.

APPLICATIONS :

Upholstery	: SWAEKASYN AM 30 - 5-6% after neutralization and before retanning.
Shoe Upper	: SWAEKASYN AM 30 - 3-5% after neutralization and before retanning SWAEKASYN AM 30 - 1-2% after fat liquoring and before fixation.
Garment	: SWAEKASYN AM30 - 3-5% after neutralization and before retanning