

Phenolic replacement tanning agent for leather

Aspect	: Light brown powder
Basis	: Phenol naphthalene condensate
Solid content	: 95±1.0%
pH	: In 10% aqueous solution, 3.0 – 4.0
Solubility	: Excellent
Light fastness	: Good
Stability	: Stable to Neutral salts, Acids and Bases in usual concentrations in tannery. Compatible with Synthetic and Vegetable tanning agents and Dyes

PROPERTIES :

- is compatible with all vegetable & synthetic tanning materials & is not sensitive to salts.
- gives excellent fullness & buff ability to the leather.
- can be used alone or in combination with vegetable and synthetic tanning agents in retanning.
- has good levelling effect on the dyeing & is particularly suitable for paler shades.
- gives good fullness, softness & uniform dyeing with medium lightfastness to the leather.
- can be used as a replacement tanning agent in all stages of tannage for the production of heavy, medium & light leather.

APPLICATIONS :

SWAEKASYN BOS can be used in all stages for the production of any articles (uppers, garment, lining etc.)

1. Upper : 3.0 – 8.0 % of SWAEKASYN BOS on shaved wt.
2. Garment : 2.0 – 4.0 % of SWAEKASYN BOS on shaved wt.
3. Light leathers : 2.0 – 6.0 % of SWAEKASYN BOS on shaved wt.
4. Sheepskins : 3.0 – 7.0 % of SWAEKASYN BOS on shaved wt.