

A neutralising agent for all types of leathers

Aspect	: Light brown free flowing powder
Basis	: Naphthalene sulphonic acid condensate
Solid content	: 95±1.0%
pH	: In 10% aqueous solution, 7.0 – 7.5
Solubility	: Completely soluble in water
Light fastness	: Excellent

PROPERTIES :

- Consists of a salt admixture, which hardly yields any hydroxyl ions but reacts almost neutral in aqueous solutions.
- Contains strongly complex-active acid radicals, which displace & buffer the sulphuric acid bound in the collagen-chromium complexes.
- Vegetable & synthetic tannins have a mild & uniform effect, imparts levelled dyeing.
- Recommended to be used together with other commonly used neutralising agents.
- Does not over neutralise the leather when used even in more quantity.
- Does not give any color reaction with iron salts.

APPLICATIONS :

In Neutralisation: (% on Sh.wt.)

: 2.0 – 2.5% SWAEKASYN PAK Run 10'

Add other Inorganic Neutralizing Salts.

In Retanning: (% on Sh. wt.)

: 1.0 – 2.0% of SWAEKASYN PAK

Along with replacement syntan or vegetable extract.