



SWAEKAFIX MO

Magnesium Oxide Based Basifying Agent

Appearance	:	Light Brown fine Powder
Nature	:	Magnesium Oxide
Concentration	:	MgO : 85-86%
pH	:	In 10% aqueous solution, 9.0 – 9.5
Solubility	:	Soluble in water

SWAEKAFIX MO

- Has a strong Complexing action with Basic Chrome Sulphate so basifying action even at very low dosage
- Unlike NaHCO_3 this product does not give erratic pH jump after feeding, so helps in gradual pH rise and so gradual basification
- Is not recommended at high dosage, otherwise result in over basification.
- Mild deliming with buffering in nature, so has less impact on grain while removal of lime

APPLICATION:

0.4 – 0.6% on pelt weight

After complete penetration of Chrome through the Cross section of Hides and skins.

It is put in 2-3 installments and after pH is achieved, left for 4-6 hrs for gradual complexing of Chrome.

In case, if in some cases, pickling pH go tremendous down, then may need 0.5% of NaHCO_3 to adjust pH, however, if it is left for some time, pH will automatically achieved and tanning is obtained.