

SWAEKASYN AM 30

Maleic Copolymer Syntan

Aspect : Clear viscous liquid

Basis : Maleic Acrylic Copolymer

Solid content : 29±1.0%

pH : In 10% aqueous solution, 7.0-8.0

Solubility : Good

Light fastness: Excellent

PROPERTIES:

- Has an excellent distribution property that protects leather from drawn grain.

- Due to its polymeric nature, it helps in achieving a unique combination of "Tight Grain with Mellow Handle".
- Is suitable for Upholstery leather, as it maintains inner softness & body even after wet toggling.
- It has a significant application in making of Shoe uppers with good inner softness and tight grain.
- Is light fast in nature, so can be used in any kind of white, pastel and other dark colored Leather.

APPLICATIONS:

Upholstery : SWAEKASYN AM 30 - 5-6% after neutralization and before retanning.

Shoe Upper : SWAEKASYN AM 30 - 3-5% after neutralization and before retanning

SWAEKASYN AM 30 - 1-2% after fat liquoring and before fixation.

Garment : SWAEKASYN AM30 - 3-5% after neutralization and before retanning