

Anionic amino resin tanning agent based on DCDA

Aspect	: Light brown free flowing powder
Basis	: Amino resin blended with anionic dispersant & inert fillers
Moisture content	: 6.0% Max.
pH	: In 10% aqueous solution, 7.0 – 8.0
Solubility	: Soluble in water with slight sediments

PROPERTIES :

SWAEKASYN IRM

- It has a selective filling action, which is mainly deposited in the loose structured parts of the leather.
- Due to less astringency, it does not disturb the grain, hence the resultant leather will be flat with fine grain.
- It tightens the grain and improves the feel of the leather .
- Improves the fullness of chrome leathers & tightens the grain
- imparts good level dyeing properties.
- Imparts good surface for buffing and embossing

APPLICATIONS :

After neutralization, at the beginning of re-tanning and before dyeing. (% based on Shaved Weight)

Sheep skins	: 2.0 – 4.0 % SWAEKASYN IRM
Goat Skin	: 1.0 – 2.0 % SWAEKASYN IRM
Garment	: 2.0 – 3.0 % SWAEKASYN IRM
Upper	: 3.0 – 5.0 % SWAEKASYN IRM