

Amphoteric Filler

Aspect	: Light Beige Powder
Basis	: Reactive Filler Based on Oxidized Soya
Moisture Content	: 6.0% Max.
pH	: In 10% aqueous solution, 4.0 – 6.0
Solubility	: Soluble in water with slight sediments

PROPERTIES

SWAEKAFILL AMB

- It has very good filling action,
- Imparts good level dyeing properties.
- Can be used as reactive filler in wet white tanning.
- It tightens the grain and improves the feel of the leather.
- Improves the fullness of chrome leather & tightens the grain
- It can be used at any stage in retanning due to its amphoteric nature.
- It helps to control double layer, when used in retaining of New Zealand & English origin sheep skins.
- Imparts good surface for buffing and embossing

APPLICATIONS

- 2.0-8.0% Based on shaved weight during retanning.
- 2.0 – 4.0% Based on pelt weight during wet white / combination tanning.